

SPEED-E OFFSET

WOODFREE OFFSET PAPER



Mill
MM Kwidzyn, Poland

1. Technical specifications

Parameter	Measurement						Unit	Standard
Substance	60 ± 2	70 ± 2	75* ± 2	80 ± 2	90 ± 2	100 ± 2	g/m ²	EN ISO 536
Moisture content	6 ± 1	6 ± 1	6 ± 1	6 ± 1	6 ± 1	6 ± 1	%	EN ISO 287
Thickness	77 ± 3	89 ± 3	96 ± 3	101 ± 3	112 ± 4	124 ± 4	µm	ISO 534
Whiteness	146 ± 3	146 ± 3	146 ± 3	146 ± 3	146 ± 3	146 ± 3	CIE	ISO 11475
Opacity	86 ± 2	90 ± 2	91 ± 2	93 ± 2	94 ± 2	95 ± 2	%	ISO 2471
Bendtsen roughness	160 ± 50	160 ± 50	160 ± 50	160 ± 50	160 ± 50	160 ± 50	cm ³ /min	ISO 8791-2
Cobb ₆₀	30	30	30	30	30	30	g/m ²	EN ISO 535
Tensile strength	4,0 +2/-1	4,0 +2/-1	4,0 +2/-1	4,0 +2/-1	4,5 +2/-1	4,5 +2/-1	kN/m	EN ISO 1924-3

2. Certificates



Please collect used paper for recycling

- 100% ECF Fibres